



ACCIAIO GLOBALE
Gazoldo degli Ippoliti
via Bresciani, 18
46040 Gazoldo Ippoliti,
Mantova - Italy
www acciaioglobale it

INSPECTION CERTIFICATE 143/0136002
ACCORDING TO : **EN 10204:2004:3.2**

CLIENTE/CUSTOMER : **TANKEEN ENERGY COMP.**
PRODOTTI/PRODUCT : **HOT ROLLED HEAVY PLATES**
GRADI DI ACCIAIO/STEEL GRADE: **P 355 NL1**
STANDARD: **EN10028-3-2017**

CERTIFICATE NO : 143/0136002
DATE : 15.03.2025

ORDINE/ORDER:
254689/11445609
SPEDIZIONE/DISPATCH:
25150223250

DIMENSIONE / DIMENSION	PLACCA / PLATE PCS.	COLATA / HEAT NO	PLACCA / PLATE NO	KG	PROVA DI TRAZIONE / TENSILE TEST				TEST D'IMPATTO / IMPACT TEST								
									joule:								
					SAM.LOC.	FLOW N/MM2	BEARING N/MM2	% UZ.080	1	2	3	AVG.	TEMP°C				
14 x 3000 x 12000	5			3961													
		399312	20253710240180		BE	367,5	582,5	22	48	40	47	45	-40				
		399312	20253710240181		BE	366,9	584,3	23	41	49	48	46	-40				
		399312	20253710240182		BE	368,0	583,3	22	42	48	47	46	-40				
		399312	20253710240183		BE	368,1	582,4	23	48	49	42	46	-40				
		399312	20253710240184		BE	367,2	582,3	22	49	42	48	46	-40				
ANALISI CHIMICA DI COLATA /CHEMICAL COMPOSITION (%) - L = Heat , P = Product																	
		COLATA HEAT NO	C %	MN %	V %	NB %	P %	S %	SI %	AL %	CU %	CR %	NI %	MO %	CEQ %	TI %	N %
		399312	0,17	0,9	0,015	0,68	0,21	0.008	0,3	0,02	0,01	0,03	0,06	0,21	0,38	0,48	0,19

Delivery condition: Normalized
Checking of marking,surface,shape and dimensions-ok Surface: EN 10163/2-2004,class B,subclass 2
Tolerance:
Sizes: EN 10029/2010,tab,1 class B,tab.2 Flatness: EN 10029/2010,class N, tab.1
Carbon equivalent formula:
CEV2 = C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15

THIRD PART INSPECTION

HEAD OF QUALITY CONTROL
ENZO FRANCESCO

SIGNATURE

